



# 250mil Geocomposite

## Geonet

Property	Test Method	Frequency	Minimum Average Roll Value
Thickness, mil (mm)	ASTM D5199	50,000 sf	250 (6.4)
Peak Tensile Strength MD, lbs./in. (N/mm)	ASTM D5035/7179	50,000 sf	55 (9.6)
Density, g/cm <sup>3</sup>	ASTM D792, Method B	50,000 sf	0.94
Carbon Black Content (%)	ASTM D4218	50,000 sf	2 - 3
Transmissivity <sup>(2)</sup> , m <sup>2</sup> /sec. (gal/min/ft)	ASTM D4716	500,000 sf	3 x 10 <sup>-3</sup> (14.5)

Notes:

- (1) Standard roll length is 250'
- (2) Transmissivity at 21°C, gradient of 0.1, load of 10,000 psf, seat time 15 min. between steel plates.
- (3) All roll widths are 14.5 feet. All roll lengths and widths have a tolerance of ±1%

All information, recommendations and suggestions appearing in this literature concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee or warranty of any kind, expressed or implied, is made by Agru/America as to the effects of such use or the results to be obtained, nor does Agru/America assume any liability in connection herewith. Any statement made herein may not be absolutely complete since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein is to be construed as permission or as a recommendation to infringe any patent.