


# Agru Tri-Lock



## Material Specifications

Agru America Tri-Lock is an extruded HDPE profile designed to provide an effective termination/attachment detail between HDPE geomembrane and concrete structures. Tri-lock is available in long lengths and is UV stabilized. It is produced from high grade resin, providing broad compatibility with HDPE lining materials.

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Method
Density	≥0.940 g/cm <sup>3</sup>	≥0.940 g/cm <sup>3</sup>	ASTM D792
Melt Index (190°C/2.16 kg)	≤1.0 g/10 min	≤1.0 g/10 min	ASTM D1238
Carbon Content (%)	≥2	≥2	ASTM D4218
Carbon Dispersion (Category)	1 or 2	1 or 2	ASTM D5596
Molded Properties	Typical Value (English)	Typical Value (SI)	Test Method
Thickness	160 mil	4 mm	ASTM D5199
Tensile Strength at Yield	88 psi	15 MPa	ASTM D6693
Tensile Strength at Break	154 psi	27 MPa	
Elongation at Yield (%)	12	12	
Elongation at Break (%)	700	700	



All information, recommendations and suggestions appearing in this literature concerning the use of our products are based upon tests and data believed to be reliable; however, it is the users responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee or warranty of any kind, expressed or implied, is made by Agru America as to the effects of such use or the results to be obtained, nor does Agru America assume any liability in connection herewith. Any statement made herein may not be absolutely complete since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein is to be construed as permission or as a recommendation to infringe any patent.