

AGRULINE Submittal and Data Sheet

- Manning Coefficient (n) = 0.009
- SDR 41 available upon request.
- Made in USA.
- Certified to:
 - NSF/ANSI/CAN 61
 - AWWA C906-21
 - ASTM D3350 Cell Class PE445574C-CC3



View the latest data here

HDPE PRESSURE PIPE SIZES

Nominal Pipe OD Size (inch)		PE4710 F714 IPS							PE4710 F714 DIPS				PE4710 F714 Metric Pipe (mm)								
		Ø24 ^{1,2}	Ø30 ^{1,2}	Ø32 ^{1,2}	Ø36 ²	Ø42 ²	Ø48 ²	Ø54 ³	Ø63 ³	Ø30 ²	Ø36 ²	Ø42 ²	Ø48 ³	Ø1800	Ø2000	Ø2250 ⁴	Ø2500 ⁴	Ø2720 ⁵	Ø2830 ⁵	Ø3260 ⁵	
SDR 9 (250 psi)	Thickness, T (inch)	2.667	3.333	3.556	4.000					3.556	4.256										
	Average, ID (inch)	18.35	22.93	24.46	27.52					24.46	29.28										
	Weight (lbs/ft)	77.8	121.6	138.4	175.2					138.4	199.0										
SDR 11 (200 psi)	Thickness, T (inch)	2.182	2.727	2.909	3.273	3.818	4.364	4.909	5.727	2.909	3.482	4.045	4.618								
	Average, ID (inch)	19.37	24.22	25.83	29.06	33.91	38.75	43.59	50.86	25.83	30.92	35.92	41.01								
	Weight (lbs/ft)	65.2	101.9	116.0	146.8	199.8	260.9	330.3	449.5	116.0	166.1	224.3	292.3								
SDR 13.5 (160 psi)	Thickness, T (inch)	1.778	2.222	2.370	2.667	3.111	3.556	4.000	4.667	2.370	2.837	3.296	3.763								
	Average, ID (inch)	20.23	25.29	26.97	30.35	35.40	40.46	45.52	53.11	26.97	32.29	37.51	42.82								
	Weight (lbs/ft)	54.2	84.7	96.4	122.0	166.0	216.8	274.4	373.5	96.4	138.1	186.4	242.9								
SDR 15.5 (138 psi)	Thickness, T (inch)	1.548	1.935	2.065	2.323	2.710	3.097	3.484	4.065	2.065	2.471	2.871	3.277								
	Average, ID (inch)	20.72	25.90	27.62	31.08	36.26	41.43	46.61	54.38	27.62	33.06	38.41	43.85								
	Weight (lbs/ft)	47.7	74.6	84.9	107.4	146.2	190.9	241.6	328.9	84.9	121.6	164.1	213.8								
SDR 17 (125 psi)	Thickness, T (inch)	1.412	1.765	1.882	2.118	2.471	2.824	3.176	3.706	1.882	2.253	2.618	2.988	4.169	4.632	5.211	5.790				
	Average, ID (inch)	21.01	26.26	28.01	31.51	36.76	42.01	47.27	55.14	28.01	33.52	38.95	44.46	62.35	69.28	77.93	86.59				
	Weight (lbs/ft)	43.8	68.4	77.9	98.6	134.1	175.2	221.7	301.8	77.9	111.6	150.6	196.2	383.9	474.1	600.1	740.6				
SDR 21 (100 psi)	Thickness, T (inch)	1.143	1.429	1.524	1.714	2.000	2.286	2.571	3.000	1.524	1.824	2.119	2.419	3.375	3.750	4.218	4.687	5.099	5.306		
	Average, ID (inch)	21.58	26.97	28.77	32.37	37.76	43.15	48.55	56.64	28.77	34.43	40.01	45.67	64.03	71.15	80.04	88.93	96.76	100.67		
	Weight (lbs/ft)	35.9	56.1	63.8	80.8	110.0	143.6	181.8	247.4	63.8	91.4	123.5	160.9	314.6	388.3	491.5	606.8	718.3	777.5		
SDR 26 (80 psi)	Thickness, T (inch)	0.923	1.154	1.231	1.385	1.615	1.846	2.077	2.423	1.231	1.473	1.712	1.954	2.726	3.028	3.407	3.786	4.119	4.285	4.936	
	Average, ID (inch)	22.04	27.55	29.39	33.06	38.58	44.09	49.60	57.86	29.39	35.18	40.87	46.66	65.41	72.67	81.76	90.84	98.84	102.83	118.46	
	Weight (lbs/ft)	29.3	45.8	52.1	65.9	89.7	117.2	148.3	201.9	52.1	74.6	100.7	131.3	256.6	316.8	401.0	495.1	586.0	634.4	841.8	
SDR 32.5 (63 psi)	Thickness, T (inch)	0.738	0.923	0.985	1.108	1.292	1.477	1.662	1.938	0.985	1.178	1.369	1.563	2.180	2.423	2.726	3.028	3.295	3.428	3.949	
	Average, ID (inch)	22.43	28.04	29.91	33.65	39.26	44.87	50.48	58.89	29.91	35.80	41.60	47.49	66.56	73.96	83.20	92.45	100.58	104.65	120.55	
	Weight (lbs/ft)	23.6	36.9	42.0	53.2	72.4	94.6	119.7	162.9	42.0	60.2	81.3	105.9	207.1	255.6	323.5	399.4	472.8	511.8	679.2	


¹ Gas Pipe Sizes per ASTM F2619

² Stripes Available

³ Stripes May be Available, Check with a Representative

⁴ System Derating Factor 0.80

⁵ System Derating Factor 0.70



OD = Outside Diameter
T = Min. Wall Thickness
Weight per foot per PPI TR-7
ID = Inside Diameter

Pipe Colors:	Black with Color Stripes:
	Blue
	Green
	Yellow

(For buried pipe only)

Note: 70ft pipe joint availability may vary depending on pipe size and production scheduling.

